

STANDARDS ASSOCIATION OF ZIMBABWE

LABORATORY REPORT

Telephone
(263-4) 753800/1/2
749180
780518
(263-4) 749181
Website: www.saz.org.zw



LABORATORIES

17 Coventry Road
Workington
Harare

This report is issued subject to the conditions printed on the reverse hereof and does not imply approval by the Standards Association of the quality and/or performance of the commodity which has been tested, nor does it entitle the holder to use the Association's Certificate Mark. The results relate only to the items tested.

Our Ref
27/11/2013

Your Ref
O/No. Cash

S. Control Dated
21/11/2013

S. Control No.
357770

Gardini Construction
219A Enterprise Road
The Grange
Chisisipite

Sample

10 x Stumble blocks (single)

Project

Determination of compressive strength

Method of Test

In accordance with SAZS 119:1994

Tests Performed By

O. Saunyama

Results:

Sample No.	Compressive Strength (MPa)	Compliance
1	5.0	Complies
2	8.0	Complies
3	5.5	Complies
4	6.3	Complies
5	9.0	Complies
6	5.4	Complies
7	5.6	Complies
8	7.7	Complies
9	5.0	Complies
10	6.3	Complies
Average	6.4	Complies

Requirements

Average compressive strength minimum requirement 3.5MPa
Individual compressive strength minimum requirement 2.8MPa

